



Technical specifications

Enduro Dryback meets the requirements of EN ISO 10582

Enduro Click Decibel meets the requirements of EN ISO 16511

Enduro Click Decibel		
	Total thickness	EN ISO 24346 5.0 mm
	Wear layer thickness	EN ISO 24340 0.55 mm
	Collection size	18
	Domestic use	EN ISO 10874 Class 23
	Commercial use	EN ISO 10874 Class 33
	Tile size	EN ISO 24342 61 x 30.5 cm
	Plank size	EN ISO 24342 121.2 x 18.5 cm
	Packaging per carton tiles	1.86 m ² (10 pcs)
	Packaging per carton planks	1.79 m ² (8 pcs)
	Squareness and straightness	EN ISO 24342 < 400 mm < 0.25 mm > 400 mm < 0.35 mm
	Total weight	EN ISO 23997 ca. 6300 g/m ²
	Wear layer binder content	EN ISO 10582 Type 1
	Castor chair continuous use	ISO 4918 Good
	Slip resistance (ramp test)	DIN 51130 R10
	Acoustical impact noise reduction	EN ISO 717-2 19 dB
	Residual indentation	EN ISO 24343-1 ≤ 0.10 mm
	Colour fastness to light	EN ISO 105-B02 method 3 ≥ 6
	Resistance to chemicals	EN ISO 26987 Good
	Dimension stability	EN ISO 23999 ≤ 0.10%
	Indoor air emissions: TVOC after 28 days	EN 16516 ≤ 0.01 mg/m ³
	Recycled content (mass)	25%
Enduro meets the requirements of EN 14041:2004		
		EN 14041 CE 0200138-010-402
	Reaction to fire	EN 13501-1 B _s -s1, L, CS
	Slip resistance	EN 13893 μ ≥ 0.30
	Thermal conductivity	EN 12524 0.25 W/mK
	Body voltage	EN 1815 ≤ 2.0 kV